iden N an delle

PCT WORLD INTELLECTUAL PROPERTY ORGANIZATION International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6:

G01T 1/26

(11) International Publication Number: WO 99/64892

(43) International Publication Date: 16 December 1999 (16.12.99)

(21) International Application Number:

PCT/IB99/01002

(22) International Filing Date:

3 June 1999 (03.06.99)

(30) Priority Data:

9812341.7

8 June 1998 (08.06.98) GB

(71) Applicant (for all designated States except US): DE BEERS INDUSTRIAL DIAMOND DIVISION (PROPRIETARY) LIMITED [ZA/ZA]; SEO Building, Comer Crownwood &

Booysens Reserve Roads, Theta, 2001 JOHANNESBURG

(ZA).

(72) Inventors; and

(75) Inventors/Applicants (for US only): SUSSMANN, Ricardo, Simon [GB/GB]; 5 Arborfield Court, Swallowfield Road, Arborfield Cross, Reading, Berkshire RG2 9JS (GB). SCARS-BROOK, Geoffrey, Alan [GB/GB]; 40 Cavendish Mead, Sunninghill, Ascot, Berkshire SL5 9TD (GB). STEWART, Andrew, David, Garry [GB/GB]; The Old Rectory, Ashampstead, Reading, Berkshire RG8 8SH (GB).

(74) Agents: GILSON, David, Grant et al.; Spoor and Fisher, P.O. Box 41312, 2024 Craighall (ZA).

(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK,


KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR,

NE, SN, TD, TG).

Published

With international search report.

(54) Title: DETECTOR FOR IONISING RADIATION



(57) Abstract

A detector for ionising radiation comprises first (10) and second (12) diamond detector elements which are connected to a common contact (14). The two detector elements are of differing thickness and are optimised for the detection of different types of radiation, so that the detector simultaneously provides two output signals indicative of different kinds of radiation incident on the detector.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	PI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	I.U	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland '
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	ΙΤ	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JР	Japan	NE	Niger	VN	Vict Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
cz	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

-1-

DETECTOR FOR IONISING RADIATION

BACKGROUND OF THE INVENTION

This invention relates to a detector for ionising radiation.

Radiation detectors comprising diamond have been proposed which are optimised for the detection of different types of radiation. For example, radiation comprising heavy particles such as alpha particles is usually absorbed close to the surface of a detector element, so that a radiation detector optimised for the detection of such radiation can be relatively thin. On the other hand, radiation such as beta particles, x-rays or gamma-rays tends to penetrate the material of a detector element to a greater depth and to be absorbed substantially uniformly throughout the bulk of the detector element.

It is an object of the invention to provide a single detector which is able to detect such different types of radiation optimally, or which can provide different types of information about a single type of radiation.

PCT/IB99/01002

WO 99/64892

-2-

SUMMARY OF THE INVENTION

According to the invention there is provided a detector for ionising radiation

comprising at least first and second diamond detector elements connected

electrically to a common contact, with respective first and second contacts

connected to the first and second detector elements, so that the detector

simultaneously provides first and second output signals corresponding to

radiation incident on the detector elements.

Preferably the first and second detector elements are optimised for the detection

of different types of radiation, or for the detection of different parameters of a

particular type of radiation.

The first and second detector elements may be formed as respective first and

second layers of diamond material in contact with a common metallic or semi-

conductor layer.

In a preferred embodiment of the invention, the first layer comprises a relatively

thick layer of diamond material and the second layer comprises a relatively thin

layer of diamond material.

The common metallic or semi-conductor layer may comprise a material selected

from the group consisting of titanium, tungsten, molybdenum and boron doped

diamond.

- 3 -

The first layer may have a thickness of between 0.3 mm and 1.5 mm and a collection distance of at least 20 μ m, preferably at least 50 μ m, and even more preferably a distance of 300 μ m or more. The first layer may be optimised for the detection of beta particles, x-rays and gamma rays.

The second layer may have a thickness of between 10 μ m and 40 μ m and may be optimised for the detection of alpha particles.

The detector may further include respective conductive layers on the outer surfaces of the first and second layers of diamond material, which preferably comprise a material selected from the group consisting of titanium, tungsten, molybdenum and boron doped diamond.

Respective active contacts may be connected to the conductive layers.

The invention also extends to a radiation detector apparatus comprising a detector as defined above, and further comprising bias means arranged to apply respective bias voltages to the first and second diamond detector elements, and first and second amplifiers having inputs connected to the first and second diamond detector elements and arranged to generate respective first and second amplified output signals corresponding to radiation incident on the detector elements

- 4 -

BRIEF DESCRIPTION OF THE DRAWING

The drawing is a highly schematic sectional view of a radiation detector

according to the invention, with associated electronic circuitry.

DESCRIPTION OF AN EMBODIMENT

The illustrated radiation detector comprises a first, relatively thick diamond

layer 10 and a second, relatively thin diamond layer 12 on either side of a layer

14 of metal or semi-conductive material which serves as a common contact or

electrode. The layers 10 and 12 are optimised for the detection of different

kinds of ionising radiation, so that a single, unitary radiation detector element is

provided which can effectively detect different types of radiation.

Alternatively, for example, the detector of the invention could be used for the

simultaneous or sequential measurement of partial energy loss of a particle

(measured in the thin layer 12) and total particle energy (measured in the thick

layer 10).

A prototype radiation detector of the invention was manufactured by

commencing with the layer 10, which was a layer of high quality diamond

produced by chemical vapour deposition (CVD) with a thickness between 0.3

mm and 1.5 mm and a collection distance of 20 μ m, but typically at least 50 μ m

and, depending on the application, possibly up to 300 μm or more.

- 5 -

Collection distance and its determination are known in the art. Radiation such as UV, x-rays and gamma rays impinging on diamond can form electron/hole pairs which drift under an applied voltage between electrodes. Typically, for penetrating radiation such as beta and gamma rays, the electrodes are placed on opposite surfaces of a diamond layer whose thickness is typically 200 - 700 µm, but can range from less than 100 µm to greater than 1000 µm, and the charge carriers (electrons/holes) drift through the thickness of the layer. For highly absorbed radiation which penetrates only a few µm into the diamond, such as alpha radiation or UV radiation with energies near or above that of the band gap, then inter-digitated electrode arrangements on the same face of the diamond layer may be used; this face may be planar or with the electrodes placed in relationship to surface structures such as grooves.

However, the electrons and holes have finite mobilities and lifetimes so they move only a certain distance before recombining. When an event occurs (e.g. impingement of beta particles) which forms charge carriers, then to first order the total signal from the detector depends on the average distance moved by the charge carriers. This charge displacement is a product of the carrier mobility and the applied electric field (which gives the charge drift velocity) and the recombination lifetime of the carriers before trapping or recombination stops its drift. This is the collection distance which can also be considered as the volume of charge swept to the electrode. The purer the diamond (or the lower the level of uncompensated traps) or the lower the level of crystalline imperfections, the higher the mobility of the carriers and/or their lifetimes.

- 6 -

The next step is the application of the conductive layer 14 to the layer 10. The conductive layer can comprise a metal which adheres to CVD diamond, such as titanium (Ti), tungsten (W), molybdenum (Mo) or other suitable metals. Alternatively, the layer 14 can comprise a substantially conductive semiconductor layer such as boron doped diamond.

The layer 12 is grown by a CVD process on top of the layer 14 to a thickness optimised for the detection of a different form of radiation compared with that for which the layer 10 is optimised. (In the prototype, the layer 10 was optimised for the detection of beta particles, x-rays and gamma-rays, while the layer 12 was optimised for the detection of alpha particles). In the prototype, the layer 12 had a thickness between 10 μ m and 40 μ m.

An alternative method of forming the radiation detector is to grow the layers 10 and 12 separately, and then to adhere the conductive layer 14 to one of these layers. The free surface of the conductive layer 14 can then be bonded to the other of the layers 10 or 12.

At one edge of the detector element, a small portion of the layer 12 was removed by a known technique such as oxygen plasma etching, ion beam milling/etching or laser ablation to expose a section 16 of the common contact/electrode 14. (Alternatively, at the time the layer 12 is grown, a section of the layer 14 may be masked. This would prevent the layer 12 from growing

-7-

on the masked section, rather than having to remove a portion of it after growth.) The section 16 serves as a common ground contact for the respective layers of the detector elements. In addition, conductive layers 18 and 20 were applied to the outer surfaces of the layers 10 and 12, respectively, to permit the connection of respective active contacts 22 and 24. The conductive layers 18 and 20 can comprise the same metal as that used for the layer 14, ie. Ti, W, Mo or other suitable metals.

The respective contacts are used to bias the respective active layers of the device and to connect the detector elements to suitable electronics.

As shown in the Figure, the contact 22 is connected to an input of a charge sensitive or operational preamplifier A_1 via a coupling capacitor C_1 while the contact 24 is connected to the input of a similar amplifier A_2 via a coupling capacitor C_2 . Respective bias voltages V_1 and V_2 are applied to the contacts 22 and 24 via resistors R_1 and R_2 . Typically, the bias voltages are 0.1 to $3V/\mu m$. The sign of the applied bias voltage (positive or negative) may vary from what is indicated in the Figure, depending on the application and the material selected for the common contact/electrode.

In a variation of the invention, the metal conductive layer 14 can be replaced by a CVD diamond boron doped layer. This has the advantage that the layer 14, and subsequently the layer 12, can both be grown epitaxially on the layer 10, resulting in the layer 12 being of a higher quality. This is because the quality

(for charge collection efficiency) is known to increase with the thickness of the layer. In the case of the above described example, the layer 12 will typically be polycrystalline in nature and will have a large component of the nucleation grain structure, which is known to be of relatively poor quality, whereas in the second example, the layer 12 will start to grow replicating the grain structure of the layer 14, which in turn should replicate that of the layer 10.

There will be a small amount of interaction between the two layers, for example, the generation of a small signal in the layer 12 due to the absorption of beta particles, but this will be in the ratio of the respective thicknesses of the layers 10 and 12, which can be made to be over a factor of 10.

In other applications, it is required to make two simultaneous measurements of the same particle(s) using a transmission detector which measures the partial energy loss in a thin transmission detector (ΔE), and total particle energy in an absorbing detector (E). From accurate measurement of both E and ΔE it is possible to calculate the mass of the particle and thus differentiate between light charged particles which have a similar mass, eg. protons, deuterons, and ³He ions. In this type of application, the requirement on the transmission detector is that it should be sufficiently thin to allow transmission of the particles of interest, which in certain applications can limit the thickness in a diamond detector to 40 μ m or less, making the detector potentially fragile. The dual detector arrangement provides both the measurement of both ΔE and E in one device, and mechanical support for the otherwise fragile ΔE detector. The latter

makes it more robust and suitable for larger areas, and also give the possibility of reducing further its thickness so that the lower energy cutoff is reduced and the energy straggling is improved. In this type of application it is important to select an interlayer of the correct thickness and properties in order to minimise the error introduced to the measure of E_1 but it does avoid the need for two separate contact layers on separate ΔE and E detectors, so that overall the system design is simplified.


The concept of the invention could easily be extended to a device having more that two detector layers. For example, such a device might be used for the detection of more than two different types of radiation of different penetration or energy loss characteristics.

CLAIMS:

- A detector for ionising radiation comprising at least first and second diamond detector elements connected electrically to a common contact, with respective first and second contacts connected to the first and second detector elements, so that the detector simultaneously provides first and second output signals corresponding to radiation incident on the detector elements.
- 2. A detector according to claim 1 wherein the first and second detector elements are optimised for the detection of different types of radiation.
- A detector according to claim 1 wherein the first and second detector elements are optimised for the detection of different parameters of a particular type of radiation.
- 4. A detector according to any one of claims 1 to 3 wherein the first and second detector elements are formed as respective first and second layers of diamond material in contact with a common metallic or semi-conductor layer.
- 5. A detector according to claim 4 wherein the first layer comprises a relatively thick layer of diamond material and the second layer comprises a relatively thin layer of diamond material.

- 6. A detector according to claim 4 or claim 5 wherein the common metallic or semi-conductor layer comprises a material selected from the group consisting of titanium, tungsten, molybdenum and boron doped diamond.
- 7. A detector according to any one of claims 4 to 6 wherein the first layer has a thickness of between 0.3 mm and 1.5 mm.
- A detector according to claim 7 wherein the first layer has a collection distance of at least 20 μm.
- 9. A detector according to claim 8 wherein the first layer has a collection distance of at least 50 μm .
- A detector according to claim 9 wherein the first layer has a collection distance of 300 μm or more.
- 11. A detector according to any one of claims 4 to 10 wherein the first layer is optimised for the detection of beta particles, x-rays and gamma rays.
- 12. A detector according to any one of claims 4 to 11 wherein the second layer has a thickness of between 10 μ m and 40 μ m.
- 13. A detector according to any one of claims 4 to 12 wherein the second layer is optimised for the detection of alpha particles.

- 14. A detector according to any one of claims 4 to 13 further including respective conductive layers on the outer surfaces of the first and second layers of diamond material.
- 15. A detector according to claim 14 wherein the conductive layers comprise a material selected from the group consisting of titanium, tungsten, molybdenum and boron doped diamond.
- A detector according to claim 14 or claim 15 including respective active contacts connected to the conductive layers.
- 17. A detector substantially as herein described with reference to the accompanying drawing.
- 18. Radiation detector apparatus comprising a detector according to any one of claims 1 to 17, bias means arranged to apply respective bias voltages to the first and second diamond detector elements, and first and second amplifiers having inputs connected to the first and second diamond detector elements and arranged to generate respective first and second amplified output signals corresponding to radiation incident on the detector elements.
- 19. Radiation detector apparatus substantially as herein described with reference to the accompanying drawing.



INTERNATIONAL SEARCH REPORT

Int :ional Application No PCT/IB 99/01002

A. CLASSII	FICATION OF SUBJECT MATTER G01T1/26		
	•		
	International Patent Classification (IPC) or to both national class	ification and IPC	
	SEARCHED cumentation searched (classification system followed by classification)	cation symbols	
IPC 6	GOIT		
Documental	tion searched other than minimum documentation to the extent th	at such documents are included in the fields se	parched .
Electronic d	ata base consulted during the international search (name of date	a base and, where practical, search terms used)
C. DOCUM	ENTS CONSIDERED TO BE RELEVANT		
Category °	Citation of document, with indication, where appropriate, of the	e relevant passages	Relevant to claim No.
Α	WO 97 00456 A (IMPERIAL COLLEGE JOHN FRANCIS (GB); GODDARD ANTO 3 January 1997 (1997-01-03) abstract		1,2, 17-19
	column 3, line 23 - column 4, column 5, line 31 - column 6, column 7, line 1 - column 8, column 13, line 4 - line 12 figures	line 18	
A	US 3 450 879 A (SEPPI EDWARD J 17 June 1969 (1969-06-17) column 1, line 51 - line 65 column 2, line 49 - line 54 column 3, line 26 - line 42 figures)	1,4, 17-19
		-/ 	
X Fur	ther documents are listed in the continuation of box C.	χ Patent family members are listed	I in annex.
° Special c	ategories of cited documents :	"T" later document published after the int	ernational filing date
consi	ent defining the general state of the art which is not dered to be of particular relevance document but published on or after the international	or priority date and not in conflict with cited to understand the principle or th invention	n the application but neory underlying the
filing "L" docum which	date ent which may throw doubts on priority claim(s) or his cited to establish the publication date of another	"X" document of particular relevance; the cannot be considered novel or cannot involve an inventive step when the d- "Y" document of particular relevance; the	ot be considered to ocument is taken alone
"O" docum	on or other special reason (as specified) nent referring to an oral disclosure, use, exhibition or means	cannot be considered to involve an in document is combined with one or m ments, such combination being obvious	nventive step when the lore other such docu-
"P" docum later	nent published prior to the international filing date but than the priority date claimed	In the art. "&" document member of the same paten	t family
Date of the	actual completion of the international search	Date of mailing of the international se	earch report
1	l1 August 1999	17/08/1999	
Name and	mailing address of the ISA European Patent Office, P.B. 5818 Patentiaan 2	Authorized officer	
	NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016	Datta, S	

Form PCT/ISA/210 (second sheet) (July 1992)

1

INTERNATIONAL SEARCH REPORT

Inti ional Application No
PCT/IB 99/01002

		PC1/1B 99/01002			
C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT					
Category *	Citation of document, with indication, where appropriate, of the relevant passages		Relevant to claim No.		
A	EP 0 381 517 A (DE BEERS IND DIAMOND) 8 August 1990 (1990-08-08) abstract column 1, line 46 - column 3, line 11 figures		1		
	·		·		
	2				

INTERNATIONAL SEARCH REPORT

Information on patent family members

Into onal Application No
PCT/IB 99/01002

Patent document cited in search report	ı	Publication date	Patent family member(s)	Publication date
WO 9700456	Α	03-01-1997	AU 6009696 A	15-01-1997
US 3450879	Α	17-06-1969	NONE	
EP 0381517	A	08-08-1990	AU 619949 B AU 4902790 A CA 2009178 A,C DE 69006224 D DE 69006224 T JP 2080186 C JP 2291178 A JP 7120813 B US 5055686 A	06-02-1992 09-08-1990 03-08-1990 10-03-1994 05-05-1994 09-08-1996 30-11-1990 20-12-1995

Form PCT/ISA/210 (patent family ennex) (July 1992)